

ALPA-LSR 120203 - Preliminary datasheet! -

Description

This is a 2-part addition cure silicone elastomer system for Liquid Injection Moulding (LSR). After mixing parts 'A' and 'B' in the correct proportions, the system will cure at elevated temperatures, usually in the range of 100 °C to 180 °C. The cycle time depends mainly on the temperature and the shape of the mould. The cured rubber exhibits excellent physical and electrical properties.

Key Features

- selfadhesive to aluminium
- low compression set

Application

ALPA-LSR 120203 is particularly suited for the production of gaskets & sealings. Self adhesive to metals without the use of primer.

In order to achieve the described properties, the vulcanization time, if a hot-air oven is used, should be at least 45 minutes at 175 °C. If a heating press is used, at least 5 minutes at 175 °C are required. In addition a postcure 4 h at 200 °C is recommended.

Use and Cure Information

IMPORTANT:

The 'A' part of product contains the platinum catalyst; great care should be taken when using automatic dispensing equipment. Please ensure that it is not contaminated by residual hydride containing rubber in the dispensing equipment, as curing will result. If in doubt, it's advised to thoroughly purge the equipment with a suitable hydrocarbon solvent or silicone fluid.

Mixing

LSR silicone elastomers usually have a very high viscosity, which is why automatic mixing and dosing equipment is recommended for mixing!

Inhibition of Cure

Great care must be taken when handling and mixing all addition cured silicone elastomer systems, ensuring that all the mixing tools (vessels, tubes and mixer) are clean and constructed in materials which do not interfere with the curing mechanism. The cure of the rubber can be inhibited by the presence of compounds of nitrogen, sulphur, phosphorus and arsenic; organotin catalysts and PVC stabilizers; epoxy resin catalysts and even contact with materials containing certain of these substances e.g. moulding clays, sulphur vulcanised rubbers, condensation cure silicone rubbers, onion and garlic.

Curing Conditions

LSR silicone elastomers do crosslink extremely slowly at room temperature. Temperatures greater than 100 °C are usually required to crosslink the materials in short time.

Health & Safety

Safety Data Sheets available on request.

Packaging

CHT Moulding Rubbers are available in a variety packaging including bulk containers. Please contact our sales department for more information.

Revision Date 12 Feb 2024
Revision No 21
Download Date 19 May 2024

Property

Uncured Product

Appearance		light blue
Color A		translucent
Color B		light blue
Cure Type		Addition
De-mould Time / Full Cure at 23°C/73°F		> 48 hrs
Density A	DIN 53 479	1.1
Density B	DIN 53 479	1.08
Mix Ratio By Weight		1:1
Viscosity A	Brookfield HBTD	350000 cP
Viscosity B	Brookfield HBTD	300000 cP
Viscosity Mixed	Brookfield HBTD	325000 cP

Cured Product

Color		Light blue
Compression Set %	BS ISO 815-1	< 25 %
Elongation at Break	DIN 53 504, S 3 A	600 %
Hardness Shore A	DIN 53 505	23,5
Linear Shrinkage (%)		< 0.1 %
Tear Resistance (N/mm)	ASTM D 624, Die B	15 N/mm / 86 ppi
Tensile Strength	DIN 53 504, S 3 A	6 N/mm2 / 870 psi

Storage

Max Storage Temperature	30 °C °C / 86 °F
Min Storage Temperature	0°C °C / 32 °F
Shelf Life	12 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com