

EM 3008 45% active silicone/silane emulsion

Description

ICM EM-3008 is a 45% active silicone/silane emulsion that can be diluted with water to achieve the desired solids for treatment. ICM EM-3008 will penetrate absorbent surfaces because of its specialized formulation, will extend the life, and preserves the appearance of above ground masonry. ICM EM-3008 is specially formulated to treat old and new brick, mortar, concrete, and concrete blocks.

Key Features

- Water based formulation
- Quick water beading with long term protection
- Ultra hydrophobic silicone/silane actives
- Deep penetration into porous substrates to extend lifetime of treated substrates.

Key Applications

- Waterproofs and hydrophobes brick, mortar, concrete, and concrete blocks
- Treats both old and new brick, mortar, concrete, and concrete blocks
- Protects from damages of water and salt

Use and Cure Information

ICM EM-3008 is typically diluted to between 5-10% actives for application. The surfaces treated should be free of dirt, oil and water. ICM EM-3008 should be applied using a sprayer or roller until the surface is completely covered and the product starts to run down. This will insure good coverage to achieve deep penetration into the concrete pores. An additional treatment can be applied after the product has been allowed to dry for several hours for enhanced protection. The product should be applied at above 5°C (40°F) and will require several hours to dry and give initial hydrophobing effect, complete cure can take up to a week, depending on conditions, with hydrophobicity increasing over time.

Health & Safety

Read product and safety data sheets before handling this product for physical and health hazard information. The safety data sheet is available from your CHT representative.

Limitations

This product is not intended for pharmaceutical use.

Revision Date	21 Sep 2021
Revision No	4
Download Date	19 May 2024

Property

Product

Appearance

Density

Ionicity

Solids Content (%)

pH

Storage

Max Storage Temperature

Min Storage Temperature

Packaging

Shelf Life

Test Method

Value

White liquid

BS ISO
2781

0.96 g/cm³

Cationic

45 %

8.5

40 °C / 104 °F

4 °C / 39 °F

40 lb. pails, 441 lb. drums,
and 2205 lb. totes

12 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com