

## QGel 300 Blue 2 part Silicone Gel

Description	Property	Test Method	Value
<p>QGels are addition-cure clear, soft, moderately cross-linked silicone polymer. Silicone gels provide protection from moisture, vibration, thermal, or mechanical shock.</p> <p><b>Key Features</b></p> <ul style="list-style-type: none"> <li>• Soft, higher strength than general purpose gels</li> <li>• One to one mix ratio</li> <li>• 24-hour room temperature cure</li> <li>• Dispensing equipment not necessary</li> </ul> <p><b>Use and Cure Information</b></p> <p><b>Important</b></p> <p>In order to achieve optimum performance, the same lot number of the A and B components should be used. Mixed lots may not obtain the performance criteria listed on the TDS or Certificate of Analysis. The "A" part of QGels contain the platinum catalyst; great care should be taken when using automated dispensing equipment to not cross-contaminate systems.</p> <p><b>Mixing</b></p> <p>Both the "A" and "B" parts should be well stirred to ensure the material is uniform. QGels should be mixed by weight. Once the components are mixed, the curing process begins. The gel time of the mixed material is listed under the typical properties. Fast curing gels should be dispensed utilizing automated mix and dispensing equipment. In order to achieve optimum performance, the same "A" and "B" side lot numbers should be used.</p> <p><b>De-Aeration</b></p> <p>Air trapped during mixing should be removed to eliminate voids in the cured product. Vacuum de-airing may be necessary to completely remove all entrapped air bubbles. To ensure proper de-airing, subject the mixed material to 29 inches of mercury.</p> <p><b>Storage and Shelf-life</b></p> <p>This product is best when used within 24 months from the date of manufacture, See product label and/or the CoA for specific "use by date". Product should be stored in its original, unopened container in an environment that does not exceed 38C (100F) Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.</p>	<b>Uncured Product</b>		
	Color A		<b>Transparent</b>
	Color B		<b>Blue</b>
	Gel Time at 25°C/77°F		<b>135 min</b>
	Viscosity A	Brookfield	<b>1,000 cP</b>
	Viscosity B	Brookfield	<b>2,000 cP</b>
	<b>Cured Product</b>		
	Penetration (19.5g Cone Weight) mm		<b>5-9 mm</b>

Revision Date 20 Oct 2021  
Revision No 1  
Download Date 19 May 2024