TECHNICAL DATA SHEET



ALPATEC 7610/60 C 2 1 part textile coating

Property

This is a 1-part, RTV (Room Temperature Vulcanizing) silicone adhesive sealant. It is one in a range of Acetoxy cure products which are solvent free. During cure, it liberates a very small amount of acetic acid, giving rise to the familiar 'vinegar' odour, which guickly dissipates after cure. It exhibits good primer-less adhesion to many substrates including but not limited to; aluminium, nonferrous metals, steel, glass, enamelled surfaces, fabrics ceramics, thermosetting, thermoplastics and wood and cures rapidly at room temperature when in contact with atmospheric moisture. This product is not to be recommended for use with galvanized metals, ferrous metals, copper and its associated alloys or in electronic assemblies.

Key Features

- Good resistance to chemicals
- Very good elongation
- Good resistance to further tearing
- High transparency

Key Applications

- Complies with Oekotex 100
- Tin free
- Solvent free

Application

Coating of stockings, narrow fabric and other textiles. ALPATEC 7610/60 C 2 is ready for use and can be processed directly from the original container e.g. by means of drum assist pumps without prior mixing. Due to the tin-free blocked catalyst the silicone paste requires temperatures of 70 - 80 °C for 30 to 40 min and 5 - 7 % air humidity for a complete, non-sticky fixation. Higher air humidity leads to a destruction of the catalyst and higher temperatures lead to a premature skin formation which inhibits the reaction, so

Uncured Product		Transparent	
Cure Profile		70 – 80 °C for 30 – 40 min. 5 - 7% BH	
Cure Type Density, uncured	DIN 53 479, 23	Acetate 1.02 g/cm3	
Flow, 20 ml	Diameter, on glass plate	80 mm	
Self Bonding	0	Yes	
Skin formation time, paper method	DIN 50 014 - 23/50-2	8 min	
Cured Product Standard climate DIN 50 014 - 23/50-2. Vulcanizate tested after 14 days			
Elongation at Break	DIN 53 504, S 3 A	300 %	
Hardness Shore A Oekotex 100	DIN 53 505	22 Yes	
Tear Resistance (N/mm)	ASTM D 624, Die B	1.7 N/mm / 10 ppi	
Storage			

Test Method

Value

Max Storage Temperature	30 °C / 86 °F
Min Storage Temperature	5 °C / 41 °F
Shelf Life	12 mths

that the silicone layer remains sticky. Thicker silicone layers prolong the curing time. A layer thickness of > 5 mm ought to be avoided. **Use and Cure Information**

This product is a ready for use 1 Part system and can be directly dispensed from the original container without mixing. If supplied in cartridges it can be applied using either manual or pneumatic dispensing guns. It can also be applied from bulk containers using conventional drum dispensing equipment.

All surfaces to which the sealant is to be applied should be clean, dry and free from grease, dust, dirt, and loose material. Priming of surfaces is not normally required but in some cases it may be necessary to pre-treat the surface. Please check this in each individual case. For degreasing of non-porous surfaces such as metal, and glass, KORASOLV GL is recommended (use undyed crepe paper or similar). If using as an adhesive, it should be applied to one clean surface and the other clean surface brought into contact with it within the stated tack free time. For optimum bond strength, the thickness of the sealant joint should be a minimum of 1 mm.

The sealant will cure upon exposure to atmospheric moisture, ideally between 20 to 70 °C and >40% humidity. Time taken for cure will depend on the thickness of the joint, humidity and temperature. Increasing the temperature and humidity will accelerate the curing process, do not cure the sealant at or above 70°C as bubbles may form in the sealant and affect the overall physical properties and adhesion. Low temperatures and humidity will retard the curing process. Since curing times progressively increase with the thickness, the sealant depth should be limited to 10 mm. Joints should be left undisturbed for at least 24 hours, but preferably longer to effect sufficient depth of cure. Full cure requires 7 days at thicknesses of 1 - 5 mm and 14 days at thicknesses of 5 - 10 mm.

"For pneumatic dispensing of 310 ml cartridges, the recommended pressure is 2.25 to 3.45 bar (40 to 50 psi). Dispensing pressure above the recommended limits may lead to gas bypassing the piston, causing spluttering at the nozzle and poor bead quality"

Solvents and cleaning agents.

For cleaning of the substrates to be bonded: KORASOLV GL.

For cleaning working tools and for removing fresh uncured material: KORASOLV GL

Care must be taken when cleaning synthetic materials which tend to form stress cracks, for example, polycarbonate and acrylic. Please contact our technical service team for advice.

For removal of vulcanized product this can be done by mechanical means or by use of a chemical digester, please contact our technical service team for advice.

Health & Safety Safety

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date29 Apr 2021Revision No1Download Date29 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht.silicones.com