

QM 100 2 part moldmaking material

Description

QM 100 is a two-component, room temperature, condensation cure, silicone material. The cured rubber is a crystal-clear material designed specifically for the special effects market. The materials' clarity allows for its use as fake ice, fake glass or any application where clarity is required.

Key Features

- Low viscosity
- Clarity
- Fast de-mold time
- Clear, pigmentable

Key Applications

- Complies with FDA indirect food contact regulation CFR 177.2600, when used with QM Cat Clear FG. Refer to QM Cat Clear FG data sheet for typical properties.

Application

Special effects, fake glass, fake ice pigmentable

Use and Cure Information

CURE CHARACTERISTICS

QM 100 should be catalyzed with QM Cat 100 at a ratio of 10:1 by weight. Faster cure can be obtained using DBT or a higher level of QM Cat 100. However, rapid cure of condensation cure moldmaking rubber often results in a small sacrifice of physical properties or an increase in hardness. The curing process begins as soon as the catalyst is mixed with the base. The material will cure as described in the data above under normal temperature (25 °C) and humidity conditions (50% RH). Because this system is sensitive to heat and humidity, a change in cure speed may be observed if one or both of these variables are altered. A large difference in temperature (+/- 5 °C) or humidity (> 60% – 70%) may alter the cure profile of the material. In addition, if the product is to be used with aggressive resins such as high styrene polyester resins, it is recommended that the rubber be allowed to cure for 48 hours.

TYPICAL PROPERTIES

UNCATALYZED		
TEST	QM 100	QM Cat 100
Appearance	Clear	Clear
Viscosity	600 cps	20 cps
Specific Gravity	0.97	0.92

CATALYZED	
MIX RATIO 10:1 by weight	
PROPERTY	RESULT
Catalyzed Color	Clear
Snap Time at 25 °C *	> 35 minutes
Demold Time	4 – 6 hours

* Snap time is defined as the time required for the material to become a solid or semi-solid.

CURED PROPERTIES	
3 DAYS at 25 °C	
Durometer, Shore A	30
Linear Shrinkage	< 0.3%

MIXING

QM 100 should be thoroughly mixed with QM Cat 100. Material should be mixed in a clean, compatible metal or plastic container. The volume of the container should be 3 – 4 times the volume of the material to be mixed. This allows for expansion of the siloxane material during de-

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

Property

Uncured Product

Cure Profile		3 days, 25°C, 50% humidity
Cure Type		Condensation
De-mould Time / Full Cure at 23°C/73°F		4 - 6 hrs
Density A	BS ISO 2781	0.97
Density B	BS ISO 2781	0.92
Mix Ratio By Weight		10:1
Rheology		Liquid
Snap Time to Become a Semi Solid at 25°C/77°F		>35 min
Viscosity Mixed	Brookfield	550 cP

Cured Product

Color		Clear
Density	BS ISO 2781	0.96 g/cm3
Hardness Shore A	ASTM D 2240-95	30
Linear Shrinkage (%)		<0.3 %

Storage

Max Storage Temperature	38 °C / 100 °F
Shelf Life	12 mths

aeration. Mix thoroughly by hand or with mixing equipment while minimizing air entrapment until a homogeneous mixture is obtained. The material will take on a uniform clear appearance.

DE-AERATION

Air trapped during mixing should be removed by vacuum at 29 inches of mercury. During the process, the material will expand, and intermittent evacuation may be required. Typically, after releasing the vacuum 2 – 3 times, the mass will collapse on itself at which time the vacuum should be left on for an additional 2 – 4 minute.

Storage

See product label and /or CoA for a specific "Use By Date". Product should be stored in its original, unopened container. Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case, the properties required for the intended use should be checked for quality assurance reasons.

Revision Date	29 Apr 2021
Revision No	1
Download Date	28 Apr 2024